

Lime putty, wood burnt

Product name	Lime putty, wood burnt Calcium hydroxide, Ca(OH) ₂ Lime putty from wood burnt and slaked lime Maturing period min. 1 year	
Producer	Holzalkbrennerei und Kalklager, D-93336 Altmannstein/Bayern	
Marketing	Kalkfabrik Netstal AG, CH-8754 Netstal/Switzerland Phone +41 55 646 91 11/Fax +41 55 646 92 66 Information: Marketing and Sales/Phone +41 55 646 92 16 E-Mail: info@kfn.ch	
Chemical analysis	Related to dry matter	
	Ca(OH) ₂	95.3 %
	CaCO ₃	5.5 %
	CaO _{total}	73.9 %
	MgO	0.6 %
	SiO ₂	0.8 %
	Fe ₂ O ₃	0.1 %
	Al ₂ O ₃	0.1 %
	Mn ₂ O ₃	< 0.1 %
	SO ₃	< 0.1 %
	Loss on ignition	26.0 %
Physical data	Density	ca. 1.4 g/cm ³
	Freezing point	0 °C
	Whiteness (Spectro Color, R _y)	91.0 %
	Beware of freezing!	
Delivery forms	Lime putty, wood burnt	in containers à 13 kg
	Lime putty, wood burnt	in containers à 40 kg
	Lime putty, wood burnt	in containers à 80 kg
Remarks	For a safe handling consult our safety data sheet. The data in this sheet are an average from numerous analyses without any legal warranty.	

